

Specifications of GraFlash anodised aluminium sheets

This is to specify the properties of products made from GraFlash anodised aluminium sheets according to the working instructions for the product which are issued by the manufacturer of the GraFlash anodised aluminium sheets i.e. Polychromal b.v., Alkmaar in Holland.

Colours	: Gold Silver (aluminium) Black BK 10 B	
Exterior Exposure	exceeding : exceeding Weatherometer Test GG-455b :	6 years for 400 hrs.
Abrasive Resistance	: Taber-Abraser with CS 17 wheel Load: 1000 gr. Cycles pro hr: 7000 : Pighairbrush + water + talcum powder. Load: 1000 gr. Cycles pro hr: up to 24000	SLIGHT DULLING NO EFFECT
Temperature Resistance	: 500°C : 300°C for 12 hrs	BLEACHING within 2 minutes. NO EFFECT
Salt spray	: 5% at 40°C for 700 hrs	NO EFFECT
Mil-S-3136 Hydrocarbon fluid	: 700 hrs immersion	NO EFFECT
Mil-S-5161 Turbine + Jet Engine fuel	: 700 hrs immersion	NO EFFECT
Kerosene	: 700 hrs immersion	NO EFFECT
Skydroll	: 700 hrs immersion	NO EFFECT
Methyl Ethylketone	: 700 hrs immersion	NO EFFECT
Ethyl acetate	: 700 hrs immersion	NO EFFECT
Xylol	: 700 hrs immersion	NO EFFECT
Heptane	: 700 hrs immersion	NO EFFECT

Ethyl alcohol	: 700 hrs immersion	NO EFFECT
Ferric chloride	: 10% solution 24 hrs	NO EFFECT
Ammonium Hydroxide	: 10% solution 10 hrs	DULLING
Mil-P-21563	: soap solution 16 hrs	NO EFFECT
Mil-C-25179 AIN in Heptane	: 25% solution, 1 min. (cleaning solution)	NO EFFECT
Sulphuric Acid	: 10% solution, 24 hrs	NO EFFECT
Phosphoric Acid	: 1% solution, 12 hrs	NO EFFECT
Nitric Acid	: 3% solution, 72 hrs	NO EFFECT
TSP	: 1% solution, 40 hrs	NO EFFECT

Alkmaar, 17-06-2016

POLYCHROMAL B.V.
Eric Hensen